

Quality Tests of PET Films

Description



- Tensile Strength (MD/TD) According to ASTM-D-882
- Elongation(MD/TD) According to ASTM-D-882
- Shrinkage @150? / 30 Minute According to ASTM-D-1204
- Haze According to **ASTM-D-1003**
- Gloss According to ASTM-D-2457
- Coefficient of Friction- uS / uK According to ASTM-D-1894
- Surface tension According to ASTM-D2578

Category

- 1. Equipment for Standards
- 2. Standards