



## Elmendorf Tear Tester

### Description

As per different standards for tear test as :

- ASTM D295, ASTM D689, ASTM D752, ASTM D4247, ASTM D1424, ASTM D1922, ASTM D5734
- TAPPI T414, TAPPI T496
- BS 2782, BS 4253, BS 4468
- CPPA D.9
- DIN 53862, DIN 53128
- ISO 1974, ISO 6383-2, ISO 9290, ISO 13937-1
- EN21974
- SCAN P11

\*\*Test results should fall between 20% and 80% of your pendulum capacity. For example, if you are using a 1600 gram pendulum, you should expect to get tear results between 1280 grams and 320 grams\*\*

- Touch-screen menu
- Easy-mount pendulums and augmenting weights
- Configurable display for results and reporting
- Thermal printer included
- Export of test results data MS EXCEL
- USB Port connections for data export
- One-touch pneumatic clamping and pendulum release