



Gel Content Tester for PEX Products

Description

- Test samples of PEX need to be immersed in boiling solvent and the insoluble part measured. The percentage of this part is degree of crosslinking //
- Round glass flask with a heating jacket //
- Cooling tower //
- Ring stand with suitable clamps and test holders with lids for the sample //
- Sample SS304 cage 50 Pcs //
- To complete the measurement you will also require a heating oven and analytical balance (will be quoted in case of customer need) //
- According to ISO 10147 , DIN 16892 , ASTM D 2765 //
- Chemicals is not included